



Almaredge™ 23

General purpose soluble metalworking fluid

Description

Castrol Almaredge™ 23 is a general purpose soluble metalworking fluid which is formulated without boron and formaldehyde releasing agents. It contains an additive package that provides good lubrication properties and performs well in a wide water range.

Almaredge 23 can be used in single sump machines as well large systems.

Application

Almaredge 23 is a versatile product recommended for general machining on low-medium alloy steel and aluminium alloys.

ü ü suggested core application ü possible application, please consult Castrol representative prior to use

	Cast Iron	Low-medium alloyed steel	High alloyed - stainless steel	Aluminium alloys	Magnesium alloys	Yellow metals
Grinding						
Milling, Turning (general machining)	ü	ü ü	ü	ü ü		ü ü
Drilling	ü	ü ü	ü	ü ü		ü ü
Reaming, Tapping	ü	ü	ü	ü		ü ü
Broaching				ü		ü ü

Advantages

- Boron free to meet boron free waste requirements
- Organic chlorine and formaldehyde releasing agent free which may help you to fulfill aspects of legislative requirem and waste treatment requirements that specify that these chemicals are exclude
- Suitable for a wide range of materials and applications provides opportunity for product consolidation
- Low foam in recommended water conditions (see details below)

Typical Characteristics

	Test Method	Unit	Almaredge 23
<u>Concentrate</u>			
Appearance	Visual		Amber
Mineral oil content	Calculated	Wt%	70
<u>Emulsion</u>			
Appearance	Visual		Milky
pH (5%)	DIN 51369 ASTM E70-97		9.0
Refractometer Factor			1.0

Subject to usual manufacturing tolerances.

Recommended Concentrations

General Machining 7-8 %
Drilling 7-10%
Reaming and Tapping 8-15%

Water range 150 – 900 ppm CaCO₃

Storage

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

For more details, please refer the product safety data sheet.

Almaredge™ 23

15 Jan 2018

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>